



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 027 897 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

16.08.2000 Bulletin 2000/33

(51) Int. Cl.⁷: **A61L 27/00**

(21) Application number: 00200458.8

(22) Date of filing: 10.02.2000

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 10.02.1999 EP 99200396

(71) Applicant: Isotis B.V.

3723 MB Bilthoven (NL)

(72) Inventors:

- Mahmood, Tahir
Cambridge, MA 02142 (US)
- Van Blitterswijk, Clemens Antoni
3467 PD Hekendorp (NL)
- Riesle, Jens Uwe
1073 XA Amsterdam (NL)

(74) Representative:

Ottevangers, Sietse Ulbe et al
Vereenigde,
Nieuwe Parkdaan 97
2587 BN The Hague (NL)

(54) **Cartilage tissue engineering**

(57) The invention relates to the use of a biodegradable, biocompatible porous matrix as a scaffold for tissue engineering cartilage, which matrix is formed of a copolymer of a polyalkylene glycol and an aromatic polyester.

EP 1 027 897 A1

Description

[0001] The invention relates to a scaffold for use in a method of tissue engineering cartilage.

[0002] The inability of articular cartilage for self-repair is a major problem in the treatment of patients who have their joints damaged by traumatic injury or suffer from degenerative conditions, such as arthritis or osteoarthritis. Examples of currently employed treatments include subchondral drilling and abrasion. However, these treatments are hardly effective in the long term, as they do not promote formation of new or replacement cartilage tissue, or cartilage-like tissue. Instead, these treatments lead to scar or fibrous tissue, which cannot withstand joint loading in the long term. Thus, although the condition of patients treated by using these conventional techniques initially improves, eventually it will deteriorate, possibly leading to osteoarthritis.

[0003] Another therapy conventionally relied on for treating loss of cartilage is replacement with a prosthetic material, such as silicone for cosmetic repairs, or metal alloys for joint relinement. Placement of prostheses is commonly associated with significant loss of underlying tissue and bone without recovery of the full function allowed by the original cartilage, as well as the irritating presence of a foreign body. Other long term problems associated with a permanent foreign body can include infection, erosion and instability.

[0004] Recently, new approaches to cartilage tissue repair have been proposed. These approaches are based on implanting or injecting expanded autologous cells per se into a defect in a patient's cartilage tissue. However, it has meanwhile been accepted that the majority of the thus implanted cells will not sustain. Also, this approach is only feasible for a relatively narrow group of patients.

[0005] Even more recent, it has been proposed in EP-A-0 469 070 to use a biocompatible synthetic polymeric matrix seeded with chondrocytes, fibroblasts or bone-precursor cells as an implant for cartilaginous structures. It is taught that it is essential that the polymeric matrix is formed of fibers or a fibrous mesh in order to provide free exchange of nutrients and waste products to the cells attached to the matrix. This free exchange is described to be particularly relevant in the stage after implantation wherein vascularization of the implant has not yet taken place. The material used for providing the polymeric matrix is a biocompatible synthetic material. The only specifically mentioned material is polyglactin 910, a 90:10 copolymer of glycolide and lactide.

[0006] The present invention aims to provide an improved scaffold for tissue engineering cartilage. It is an object to provide an artificial matrix which is highly suitable to serve as a temporary scaffold for cellular growth and implantation of cartilage. The matrix should be biodegradable and non-toxic and enable cell growth

both in vivo and in vitro. It is a further object that the scaffold can provide sufficient mechanical strength for it to be utilized for cell growth to replace degenerated cartilage in joints, and desirably also to withstand joint loading. It should further be possible to design the scaffold such that it is suitable to replace hyaline or elastic cartilage in plastic and reconstructive surgery.

[0007] Surprisingly, it has been found that the above objectives are fulfilled by using a porous matrix of a specific polymeric material as a scaffold for engineering cartilage tissue. Thus, the invention relates to the use of a biodegradable, biocompatible porous matrix as a scaffold for tissue engineering cartilage, which matrix is formed of a copolymer of a polyalkylene glycol and an aromatic polyester.

[0008] The material used as a scaffold in accordance with the invention meets all the above requirements for use in cartilage repair or replacement. In particular, said material provides superior mechanical strength so that the scaffold is able to withstand joint loading to a degree which is not attainable using a fibrous structure.

[0009] Furthermore, the specific polymeric material on which the present scaffold is based has hydrogel properties and allows for diffusion through the material itself, in addition to diffusion through its porous structure. Of course, this feature is highly advantageous when cells are seeded onto the scaffold and are cultured thereon, as it enables a very efficient transport of nutrient and waste materials from and to the cells. Secondly, the material closely mimics the structure and properties of natural cartilage, which, containing 80% water, is also a hydrogel. Furthermore, the swelling behavior of the specific polymeric material allows for optimal fixation of the structure in a defect when it is implanted without cells seeded thereto in vitro.

[0010] A matrix to be used as a scaffold in accordance with the invention is biodegradable and biocompatible. In the context of the present invention, the term biocompatible is intended to refer to materials which may be incorporated into a human or animal body substantially without unacceptable responses of the human or animal. The term biodegradable refers to materials which, after a certain period of time, are broken down in a biological environment. Preferably, the rate of breakdown is chosen similar or identical to the rate at which the body generates autogenous tissue providing sufficient mechanical strength to replace the implant of which the biodegradable material is manufactured.

[0011] In accordance with the invention, the matrix has a slower rate of degradation in a biological environment than the copolymers of glycolide and lactide which are preferred according to the above discussed EP-A-0 469 070, ensuring mechanical support over the whole regeneration period in vivo before the extracellular matrix synthesized by cells seeded onto the scaffold, or by cells of the surrounding tissue present in vivo, takes over the mechanical function.

[0012] Further, the present matrix is porous (i.e. non-fibrous). This means that the matrix is a substantially homogeneous, solid structure, provided with small holes (pores), which enable diffusion of nutrients and waste products. As opposed to a fibrous structure, which is composed of different elements (fibers), the present porous matrix is a continuous structure, substantially composed of one element, comprising distinct compartments. It is preferred that the pores in the present matrix are interconnected.

[0013] Preferably, the matrix has a macroporosity between 30 and 99%, more preferably between 60 and 95%. The pores in the matrix preferably have a diameter of between 0.1 and 2000 μm , more preferably between 1 and 1000 μm . The macroporosity and the diameter of the pores will be chosen such that, on the one hand, sufficient diffusion of nutrients and waste products can take place, and, on the other hand, sufficient mechanical strength is provided by the matrix.

[0014] As has been mentioned, the present scaffold is formed of a specific class of polymeric materials having hydrogel properties. This is the class of copolymers of a polyalkylene glycol and an aromatic polyester. Preferably, these copolymers comprise 40-80 wt.%, more preferably 50-70 wt.% of the polyalkylene glycol, and 60-20 wt.%, more preferably 50-30 wt.% of the aromatic polyester. A preferred type of copolymers according to the invention is formed by the group of block copolymers.

[0015] Preferably, the polyalkylene glycol has a weight average molecular weight of from 150 to 4000, more preferably of 200 to 1500. The aromatic polyester preferably has a weight average molecular weight of from 200 to 5000, more preferably of from 250 to 4000. The weight average molecular weight of the copolymer preferably lies between 20,000 and 200,000, more preferably between 50,000 and 120,000. The weight average molecular weight may suitably be determined by gel permeation chromatography (GPC). This technique, which is known per se, may for instance be performed using tetrahydrofuran as a solvent and polystyrene as external standard.

[0016] In a preferred embodiment, the polyalkylene glycol component has units of the formula $-\text{OLO}-\text{CO}-\text{Q}-\text{CO}-$, wherein O represents oxygen, C represents carbon, L is a divalent organic radical remaining after removal of terminal hydroxyl groups from a poly(oxyalkylene)glycol, and Q is a divalent organic radical.

[0017] Preferred polyalkylene glycols are chosen from the group of polyethylene glycol, polypropylene glycol, and polybutylene glycol and copolymers thereof, such as poloxamers. A highly preferred polyalkylene glycol is polyethylene glycol.

[0018] The terms alkylene and polyalkylene generally refer to any isomeric structure, i.e. propylene comprises both 1,2-propylene and 1,3-propylene, butylene comprises 1,2-butylene, 1,3-butylene, 2,3-butylene, 1,2-isobutylene, 1,3-isobutylene and 1,4-isobutylene

(tetramethylene) and similarly for higher alkylene homologues. The polyalkylene glycol component is preferably terminated with a dicarboxylic acid residue $-\text{CO}-\text{Q}-\text{CO}-$, if necessary to provide a coupling to the polyester component. Group Q may be an aromatic group having the same definition as R, or may be an aliphatic group such as ethylene, propylene, butylene and the like.

[0019] The polyester component preferably has units $-\text{O}-\text{E}-\text{O}-\text{CO}-\text{R}-\text{CO}-$, wherein O represents oxygen, C represents carbon, E is a substituted or unsubstituted alkylene or oxydialkylene radical having from 2 to 8 carbon atoms, and R is a substituted or unsubstituted divalent aromatic radical.

[0020] In a preferred embodiment, the polyester is chosen from the group of polyethylene terephthalate, polypropylene terephthalate, and polybutylene terephthalate. A highly preferred polyester is polybutylene terephthalate.

[0021] It is believed that the use of a copolymer of polyethylene glycol, having a weight average molecular weight of between 800 and 1200 (preferably 1000) and polybutylene terephthalate in a weight ratio of between 65 to 35 and 75 to 25 (preferably 70 to 30) may lead to a faster proliferation of cells, such as chondrocytes, seeded on a scaffold of said copolymer.

[0022] The preparation of the copolymer will now be explained by way of example for a polyethylene glycol/polybutylene terephthalate copolymer. Based on this description, the skilled person will be able to prepare any desired copolymer within the above described class. An alternative manner for preparing polyalkylene glycol/polyester copolymers is disclosed in US-A-3,908,201.

[0023] A polyethylene glycol/polybutylene terephthalate copolymer may be synthesized from a mixture of dimethyl terephthalate, butanediol (in excess), polyethylene glycol, an antioxidant and a catalyst. The mixture is placed in a reaction vessel and heated to about 180°C, and methanol is distilled as transesterification proceeds. During the transesterification, the ester bond with methyl is replaced with an ester bond with butylene. In this step the polyethylene glycol substantially does not react. After transesterification, the temperature is raised slowly to about 245°C, and a vacuum (finally less than 0.1 mbar) is achieved. The excess butanediol is distilled and a prepolymer of butanediol terephthalate condenses with the polyethylene glycol to form a polyethylene/polybutylene terephthalate copolymer. A terephthalate moiety connects the polyethylene glycol units to the polybutylene terephthalate units of the copolymer and thus such copolymer also is sometimes referred to as a polyethylene glycol terephthalate/polybutylene terephthalate copolymer (PEGT/PBT copolymer).

[0024] A porous structure of the polymeric material may be obtained by any known method, such as salt leaching or sintering. In principle, any combination of techniques, such as phase inversion, freeze drying and salt leaching may be used.

[0025] In a salt leaching procedure, the scaffold material may be subjected to a solvent casting procedure, wherein a substrate is formed by liquefying the material in a suitable solvent containing salt particles having a suitable particle size to acquire the desired pore size. The salt/polymer solution may then be cast on a plate using a substrate-casting apparatus fixed at a certain height finally leading to the desired thickness of the structure to be formed. The salt particles are then leached out of the copolymer by washing with, for instance (distilled) water.

[0026] It is also possible to use a viscous polymer gel in the salt leaching procedure, instead of a polymeric solution. In that case, the first step of the procedure is the preparation of a relatively concentrated polymer solution (preferably comprising at least 50 wt.% of the polymer) at elevated temperatures, such as from 60 to 120°C. Preferred solvents have a relatively high boiling point, and are miscible with water. An example of a solvent which has been found to particular good results is N-methylpyrrolidone. In the second step of the procedure, salt particles are added to the polymer solution. Subsequently, the solution is transferred into a mould, having the desired shape and size of the scaffold to be formed, and is cooled to room temperature. Upon cooling, a stable polymer gel is formed. Placement of the gel in demineralized water leads to removal of the solvent and the salt, resulting in a stable porous material.

[0027] In a sintering procedure, the scaffold material may be placed into a mold and subsequently heated under pressure to a temperature below the melting point of the material. Releasing the pressure and cooling the material yields a sintered product. The skilled person may, based on his general knowledge, adapt the conditions during the sintering procedure such that the desired porous structure is obtained.

[0028] Yet another advantage of the specific polymeric material of which the present scaffold is formed is that it is possible to incorporate bioactive agents in said material, which agents are slowly released upon degradation of the material in vivo. In this regard, reference is made to the US patent 5,980,948, the contents of which are incorporated herein by reference.

[0029] In a preferred embodiment, the outer surface of the scaffold is partly or completely provided with a ceramic coating. Preferably, the ceramic coating is a calcium phosphate coating. It has been found that the presence of a ceramic coating is highly beneficial to the attachment of cells to the scaffold. The calcium phosphate may be applied to the polymeric material by soaking said material into a highly concentrated calcifying solution at low temperature. The calcifying solution is preferably composed of at least calcium and phosphate ions, and optionally of magnesium, carbonate, sodium and chloride ions, which are dissolved into water by bubbling carbon dioxide gas. During the natural release of carbon dioxide gas or its exchange with air, the pH of

the calcifying solution is increased and the saturation is raised until the nucleation of carbonated calcium phosphate crystals on the surface of the scaffold. The process of bubbling / releasing CO₂ gas through or from the calcifying solution can be repeated until a sufficient thickness of the coating has been reached. In general, the thickness of the ceramic layer will be between 0.1 and 20 µm. It is preferred, that the ceramic coating is designed such that it has its beneficial effect during the seeding of cells onto the scaffold, and during the subsequent in vitro culturing of said cells. It is further preferred, that, by the time the scaffold is to be implanted into a patient's body, the ceramic coating has substantially disappeared. This may for instance be accomplished through the presence of the cells or culture medium, e.g. by dissolution.

[0030] Under certain conditions, particularly when the scaffold is intended to be used in the treatment of full-thickness cartilage defects, comprising cartilage as well as bone, it has been found advantageous to use a composite scaffold comprising a first part which has an outer surface of a polymeric material, of the above discussed type, and second part which has an outer surface of a ceramic material. The composite matrix preferably is a two-layer system, wherein the ceramic part mimics the function of bone, and the polymeric part mimics the function of cartilage. Thus, the composite matrix mimics the nature of both cartilage and bone tissue. Furthermore, the ceramic outer surface facilitates adhesion of cells to the scaffold both in vitro and in vivo.

[0031] The first part of the composite matrix, is preferably substantially in its entirety formed of a copolymer of the above discussed type. The second part of the composite matrix may be substantially completely formed of a ceramic material. Examples of suitable ceramic materials include calcium phosphate, calcium carbonates, and sodium calcium phosphates. Particularly suitable ceramic materials are chosen from the group of octacalcium phosphate, apatites, such as hydroxyapatite and carbonate apatite, whitlockites, such as α-tricalcium phosphate, β-tricalcium phosphate, sodium calcium phosphate, and combinations thereof. It is also possible that the second part is formed of a different material, but coated with a ceramic material as set forth herein above. The said different material may be any type of polymeric material, preferably the above discussed copolymer of a polyalkylene glycol and an aromatic ester, or another suitable material, such as Bioglass or a glass-ceramic.

[0032] In a preferred embodiment, a dense layer, preferably of the above discussed copolymer of a polyalkylene glycol and an aromatic ester, is applied between the polymeric and ceramic parts to avoid movement of cells from one part to the other.

[0033] The composite may be prepared in any suitable manner, for instance by providing a mould having the desired shape of the composite scaffold. The ceramic part of the composite, which is prepared sepa-

ately, may be placed in the mould, and the polymeric layer may be cast on top of the ceramic part, e.g. by injection moulding. It is also possible to apply the polymeric part in the form of a polymer-salt solution, which is used in the above described salt leaching procedure for achieving the desired porosity. Optionally, the dense layer may be applied onto the ceramic part first. A good attachment is obtained between the ceramic and polymeric parts of the composite as the polymeric material will invade the pores of the ceramic part to some extent during injection moulding.

[0034] A scaffold based on a biodegradable, biocompatible, porous matrix as described above, which is of course also encompassed by the present invention, may be used in tissue engineering cartilage with or without cells seeded thereon in vitro. The scaffold may be processed to have a particular desired form in any known manner. The matrix being formed of a polymeric material having hydrogel properties, the swelling behavior or the scaffold allows for swell fixation of the implant in a defect in cartilage tissue into which it is implanted. This swell fixation is specifically advantageous when the scaffold is implanted cell free. The extent of swelling can suitably be controlled by adjusting the composition of the polymeric material.

[0035] In a preferred embodiment, the scaffold is seeded with cells prior to its implantation. The cells may be any type of cells commonly occurring in natural cartilage or any type of cells capable of differentiating into cells commonly occurring in natural cartilage. Preferred cell types are chondrocytes, bone-precursor cells, stem cells, and cells of periosteum or perichondrium tissues. These cells may also be used in their crude form, e.g. in the form of bone marrow, comprising more than one cell type or even extracellular matrix. It is further preferred that the cells are autologous cells, thus minimizing, or even excluding, the chance of rejection responses in or disease transmission (e.g. HIV) to the patient treated with the present scaffold.

[0036] The seeding may be carried out in any known manner, for instance by static seeding. It is preferred, however, that the cells are seeded dynamically as has been described in co-pending European patent application 98203774.9, which is incorporated herein by reference. Subsequent to the seeding process, the cells are preferably cultured in vitro, allowing for a sufficient degree of proliferation and/or differentiation of the cells. The period required for culturing may vary broadly and range between one hour and several months, dependent on the number of seeded cells and the size of the implant required.

[0037] The invention further relates to the use of the above scaffold as a medical implant in cartilage repair. This use may specifically apply in cases of damaged cartilage in a patient as a result of inflammation, trauma, aging, or wherein the cartilage is congenitally defective.

[0038] The invention will now be elucidated by the following, non-restrictive example.

EXAMPLE

[0039] Human chondrocytes were isolated from articular cartilage and seeded on a porous Polyactive scaffold (55/45(300), 1.55 cm diameter, 300 μ m thick discs, macroporosity 75%). The chondrocytes were dynamically seeded onto the scaffold for 24 hours and cultured for 20 days in flasks using a magnetic stirrer at 45 rpm. Thus, both the seeding and the culturing were performed under dynamic conditions. The culture medium comprised Dulbecco's modified Eagle medium (DMEM) containing 4.5 g/L glucose, 584 mg/L glutamine, 10% Fetal Bovine Serum (F, 50 U/mL penicillin), 50 μ g/mL streptomycin, 10 mM N-2hydroxyethylpiperazine N'-2-ethanesulfonic acid (HEPES), 0.1 mM non-essential amino acids, 0.4 mM proline and 50 μ g/mL ascorbic acid.

[0040] Samples were taken for SEM (Scanning Electron Microscopy) and LM (Light Microscopy) analysis 3, 10 and 20 days after seeding. After 3 days, both SEM and stereo LM (allowing for 3-dimensional analysis) showed pronounced cell attachment and ingrowth. After 20 days, homogeneous cell distribution within the matrix and ECM formation were observed.

Claims

1. Use of a biodegradable, biocompatible, porous matrix as a scaffold for tissue engineering cartilage, which matrix is formed of a copolymer of a polyalkylene glycol and an aromatic polyester.
2. Use according to claim 1, wherein the scaffold is provided with chondrocytes, bone-precursor cells, stem cells, or cells of periosteum or perichondrium tissue.
3. Use according to claim 1 or 2, wherein the polymeric material is a copolymer of polyethylene glycol and poly(butylene terephthalate).
4. Use according to any of the preceding claims, wherein the matrix comprises a calcium phosphate coating.
5. Use according to any of the preceding claims, wherein the matrix is a composite comprising a first part which has an outer surface of a polymeric material, and a second part which has an outer surface of a ceramic material.
6. Use according to claim 5, wherein the ceramic material is a calcium phosphate coating or chosen from the group of octacalcium phosphate, apatites, such as hydroxyapatite and carbonate apatite, whitlockites, such as α -tricalcium phosphate, β -tricalcium phosphate, sodium calcium phosphate, and combinations thereof.

7. Biodegradable, biocompatible, porous matrix formed of a copolymer of a polyalkylene glycol and an aromatic polyester to be used as a scaffold for tissue engineering cartilage according to any of the preceding claims. 5
8. Matrix according to claim 7 provided with chondrocytes, bone-precursor cells, stem cells or cells of periosteum or perichondrium tissue. 10
9. Method for repairing cartilage comprising implantation of a scaffold according to claim 7 or 8.
10. Use of a biodegradable, biocompatible, porous matrix formed of a copolymer of a polyalkylene glycol and an aromatic polyester for the manufacture of a scaffold for implantation in a patient for repairing cartilage. 15
11. Cartilage implant comprising a matrix according to claim 7 and having cartilage tissue. 20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 20 0458

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	EP 0 714 666 A (ETHICON INC) 5 June 1996 (1996-06-05) * the whole document *	2,4,6,8	A61L27/00
Y	WO 98 22154 A (TISSUE ENG INC (US)) 28 May 1998 (1998-05-28) * examples * * claims *	2,4-6,8	
A	WO 97 17038 A (UNIV MASSACHUSETTS) 15 May 1997 (1997-05-15) * the whole document *	1-11	
X	WO 93 21858 A (OSTEOTECH INC) 11 November 1993 (1993-11-11) * abstract *	1,3,7, 9-11	
Y	* page 2, paragraph 2 - page 6, paragraph 3 *	2,4-6,8	
	* examples		
A	US 5 821 285 A (KHOR E. ET AL) 13 October 1998 (1998-10-13) * the whole document *	1-11	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			A61L
A	US 5 674 292 A (TUCKER MARJORIE M ET AL) 7 October 1997 (1997-10-07) * column 8, line 20 - column 9, line 11 * * column 12, line 62 - column 13, line 67 *	1-3,7-11	
X	EP 0 357 155 A (STICHTING TECH WETENSCHAPP) 7 March 1990 (1990-03-07) * the whole document * especially example 1	1-11	
X	EP 0 891 783 A (ISOTIS B V) 20 January 1999 (1999-01-20) * the whole document *	1-11	
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 17 March 2000	Examiner Panzica, G
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04031)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 20 0458

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-03-2000

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0714666	A	05-06-1996	AU 3795395 A	06-06-1996
			BR 9505580 A	04-11-1997
			CA 2164045 A	31-05-1996
			JP 8215299 A	27-08-1996
			US 5747390 A	05-05-1998
			US 5679723 A	21-10-1997
WO 9822154	A	28-05-1998	US 5891558 A	06-04-1999
			AU 5261698 A	10-06-1998
			EP 0946127 A	06-10-1999
WO 9717038	A	15-05-1997	AU 1051597 A	29-05-1997
			EP 0906069 A	07-04-1999
			US 5944754 A	31-08-1999
WO 9321858	A	11-11-1993	AU 5155493 A	29-11-1993
			CA 2118520 A	11-11-1993
			EP 0637229 A	08-02-1995
			JP 7505813 T	29-06-1995
			NO 944011 A	21-10-1994
			US 5508036 A	16-04-1996
			US 5480436 A	02-01-1996
US 5821285	A	13-10-1998	SG 60017 A	22-02-1999
US 5674292	A	07-10-1997	AU 6333596 A	30-12-1996
			CA 2223049 A	19-12-1996
			EP 0837701 A	29-04-1998
			JP 11506360 T	08-06-1999
			WO 9640297 A	19-12-1996
			US 6013856 A	11-01-2000
EP 0357155	A	07-03-1990	NL 8802178 A	02-04-1990
			AT 105490 T	15-05-1994
			DE 68915229 D	16-06-1994
			DE 68915229 T	17-11-1994
			ES 2056195 T	01-10-1994
			KR 140538 B	15-06-1998
EP 0891783	A	20-01-1999	CA 2243248 A	16-01-1999

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82